Synthesis and sintering of nano-sized BaSnO₃ powders containing BaGeO₃

Roberto Köferstein^{a,*}, Lothar Jäger^a, Mandy Zenkner^a, Francisco Javier García-García^b,

Stefan G. Ebbinghaus^a

^a *Institut für Chemie, Anorganische Chemie, Martin-Luther-Universität Halle-Wittenberg,
Kurt-Mothes Strasse 2, D-06120 Halle, Germany*

^b *Lehrstuhl für Festkörperchemie, Institut für Physik, Universität Augsburg,
Universitätsstrasse 1, D-86159 Augsburg, Germany*

* Corresponding author. Tel.: +49-345-5525630; Fax: +49-345-5527028.
E-mail address: roberto.koefenstein@chemie.uni-halle.de

Abstract. The formation of solid solutions of the type [Ba(HOC₂H₄OH)₄][Sn_{1-x}Ge_x(OC₂H₄O)₃] as BaSn_{1-x}/Ge_xO₃ precursor and the phase evolution during its thermal decomposition are described in this paper. The 1,2-ethanediolato complexes can be decomposed to nano-sized BaSn_{1-x}/Ge_xO₃ preceramic powders. Samples with $x = 0.05$ consist of only a Ba(Sn,Ge)O₃ phase, whereas powders with $x = 0.15$ and 0.25 show diffraction patterns of both the Ba(Sn,Ge)O₃ and BaGeO₃ phase. The sintering behaviour was investigated on powders with a BaGeO₃ content of 5 and 15 mol%. These powders show a

specific surface area of 15.4–15.9 m²/g and were obtained from calcination above 800 °C. The addition of BaGeO₃ reduced the sintering temperature of the ceramics drastically. BaSn_{0.95}Ge_{0.05}O₃ ceramics with a relative density of at least 90 % can be obtained by sintering at 1150 °C for 1 h. The ceramic bodies reveal a fine microstructure with cubical-shaped grains between 0.25–0.6 μm. For dense ceramics the sintering temperature could be reduced down to 1090 °C, when the soaking time was extended up to 10 h.

Keywords: *BaSnO₃; BaGeO₃; precursor; thermal decomposition; ceramic; sintering*

1. Introduction

Pure and doped barium stannate (BaSnO₃) as well as its solid solutions (e.g. BaTi_{1-x}Sn_xO₃) have found important applications in materials science and technology due to its dielectric properties, semiconducting behaviour and high thermal stability [1,2,3]. Because of these characteristic properties, BaSnO₃ based ceramics are becoming more and more important in materials technology. For example, BaSnO₃ can be used to prepare thermally stable capacitors and to fabricate ceramic boundary layer capacitors [4,5,6,7,8,9,10,11,12]. Furthermore, BaSnO₃ can be also used as a functional material for semiconductor gas sensors and photocatalytic applications [13,14,15,16,17,18,19,20]. BaSnO₃ crystallises in the perovskite-type structure and has a band gap of 3.4 eV [21]. Apart from the mixed-oxide method, which results in coarse-grained powders, some chemical syntheses have been developed to obtain fine-grained BaSnO₃ powders. Hydrothermal and sol-gel [22,23,24,25] synthesis as well as precursor complex, coprecipitation- and polymerised complex methods [26,27,28,29] are suitable to obtain fine-grained BaSnO₃ powders. Compacts on the basis of BaSnO₃ generally reveal only a moderate densification behaviour [5,30,31,32,33,34,35,36,37]. Therefore, such ceramic bodies need high sintering temperatures or very long soaking times. In order to

produce capacitor components based on BaSnO₃, dense (i.e. almost pore free) material bodies are required, because pores would act as a sink to the electrical charge carriers and would be the source of poor grain-to-grain connectivity and significant dielectric losses [34,35,38,39,40,41,42]. The densification behaviour can be improved and thus the sintering temperature can be reduced using fine-grained powders [30] or sintering aids [43,44]. *Kumar* and *Choudhary* [45] sintered coarse-grained BaSnO₃ adding BaSiO₃, while *Wang et al.* [46] used SiO₂ as a sintering aid for BaSnO₃. Recently, we have investigated the effect of BaGeO₃ on the sintering properties and microstructures of both BaSnO₃ ceramic bodies prepared by the classical mixed-oxide method [47] and BaTiO₃-based ceramics [48].

The present study deals with the preparation of a Ba(Sn,Ge)-1,2-ethanediolato complex precursor, including a sintering aid component, which can be decomposed to nano-sized BaSn_{1-x}/Ge_xO₃ powders. In this precursor the components are evenly distributed on a molecular level, which leads to a more homogeneous distribution of the sintering aid in the resulting ceramic bodies. Additionally, phase evolution, the sintering behaviour of BaSn_{1-x}/Ge_xO₃ compacts as well as the microstructures of resulting ceramic bodies have been investigated.

2. Experimental

2.1. Material preparation

[Ba(HOC₂H₄OH)₄][Sn_{1-x}Ge_x(OC₂H₄O)₃] precursor complexes were prepared analogously to the preparation of [Ba(HOC₂H₄OH)₄][Sn(OC₂H₄O)₃] [30]. Ice-cold water (800 mL) was slowly added to fresh distilled SnCl₄ (0.10-*x* mol; p.a., *Laborchemie Apolda*) and then a concentrated ammonia solution was added to adjust a pH value of 7–7.5. The precipitate was slowly filtered off and washed with water until the filtrate was almost free from Cl⁻ ions. A suspension of this wet precipitate (SnO₂ · *n* H₂O) with Ba(OH)₂ · 8H₂O (0.10-*x* mol; puriss. p.a., *Fluka*) and 800 mL 1,2-ethanediol was stirred overnight at room temperature in an argon

atmosphere. Thereafter, the suspension was heated at about 130 °C to remove water. Afterwards $\text{Ge}(\text{OC}_2\text{H}_5)_4$ (x mol, *Alfa Aesar GmbH & Co KG*) and x mol $\text{Ba}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$ were added. The reaction mixture was heated at 120–130 °C for 8 h. About $\frac{2}{3}$ of the solvent was removed under reduced pressure at about 80 °C. The reaction mixture was then cooled to room temperature and diluted with propan-2-ol. The white, crystalline precipitate of $[\text{Ba}(\text{HOC}_2\text{H}_4\text{OH})_4][\text{Sn}_{1-x}\text{Ge}_x(\text{OC}_2\text{H}_4\text{O})_3]$ was filtered, washed with acetone and dried at room temperature in vacuum.

For the shrinkage and sintering studies the precursor complexes with $x = 0.05$ and 0.15 were calcined in static air at 850 and 860 °C by a heating rate controlled thermal treatment, as described below. The calcined powders were milled with ZrO_2 -balls in propan-2-ol for 2 h ($m_{\text{powder}}:m_{\text{balls}} = 1:4$). After filtering and drying, the powders were mixed with 5 mass% of a saturated aqueous solution of polyvinyl alcohol (PVA) as a pressing aid, then the powders were pressed to discs with a green density of about 2.8–3.0 g/cm³.

2.2. Characterization

X-ray powder diffraction (XRD) patterns were recorded on a *STOE STADI MP* diffractometer at 20 °C using $\text{Co-K}\alpha_1$ radiation. Dilatometric (shrinkage) investigations were performed in a flowing synthetic air atmosphere (50 ml/min) in a TMA 92-16.18 unit from *Setaram*. The specific surface area was determined using nitrogen three-point BET (Nova 1000, *Quantachrome Corporation*). The equivalent BET particle diameter was calculated assuming the powder particles were spherical or cubic in shape [49]. Crystallite sizes were determined with the software suite WinXPOW [50] by XRD line broadening using the Scherrer equation [51] and the integral peak breadth. Scanning electron microscope images were recorded with a *Philips XL30 ESEM* (Environmental Scanning Electron Microscope) and transmission electron microscope images were recorded with a *Jeol JEM 2100F*.

3. Results and discussion

3.1. Solid solutions of the type $[Ba(HOC_2H_4OH)_4][Sn_{1-x}Ge_x(OC_2H_4O)_3]$

The non-isotypic 1,2-ethanediolato complexes $[Ba(HOC_2H_4OH)_4][Sn(OC_2H_4O)_3]$ (**1**) and $[Ba(HOC_2H_4OH)_2Ge(OC_2H_4O)_3]$ (**2**) can be used as precursors for fine-grained $BaSnO_3$ and $BaGeO_3$ powders [30,52,53]. We have prepared mixed precursor complexes of **1** and **2** up to a germanium content of 25 mol%. Since the XRD patterns of the $Ba(Sn,Ge)$ -precursor complexes (Fig. 1b-d) show only the reflection pattern of complex **1** (Fig. 1a) it can be concluded that each precursor consists of a single phase indicating the formation of solid solutions of the type $[Ba(HOC_2H_4OH)_4][Sn_{1-x}Ge_x(OC_2H_4O)_3]$ up to $x = 0.25$. Furthermore, the insertion of Ge^{4+} into the crystal structure of **1** is connected to a decrease in unit cell volume (inset in Fig. 1).

Fig. 2 represents XRD patterns of $[Ba(HOC_2H_4OH)_4][Sn_{0.75}Ge_{0.25}(OC_2H_4O)_3]$ (**25**, the number represents the germanium content) after different calcination steps in static air (heating rate 10 °C/min). Analogous to the calcination of the complexes **1** and **2**, precursor **25** disintegrated into $BaCO_3$, SnO_2 and GeO_2 at 500 °C. The XRD pattern (Fig. 2a) clearly shows reflections of orthorhombic $BaCO_3$ and tetragonal GeO_2 [54]. The reflection at $2\theta = 31.0^\circ$ represents tetragonal SnO_2 and possibly hexagonal GeO_2 [54]. Heating at 650 °C (Fig. 2b) leads to a reduction of the intensities of reflections representing SnO_2 and GeO_2 . The broad reflection around $2\theta = 35.5^\circ$ indicates the evolution of $BaSnO_3$ [54]. Calcination at 700 °C for 1 h results in strong reflections of $BaSnO_3$, whereas the reflection for tetragonal GeO_2 disappears (Fig. 2c). XRD pattern after a heat treatment at 900 °C reveals the formation of orthorhombic $BaGeO_3$ (not shown) and at 1000 °C we clearly observe reflections of $BaSnO_3$ and orthorhombic $BaGeO_3$ (Fig. 2d). The small amount of $BaCO_3$ completely vanished above 1000 °C (Fig. 2e). In ref. [47] it was observed a partial solid solubility of $BaGeO_3$ in $BaSnO_3$ of the order of 6–7 mol%. Therefore, the reflections of $BaSnO_3$ represent the perovskite phase $Ba(Sn,Ge)O_3$.

3.2. Shrinkage and sintering behaviour

Preceramic powders with BaGeO₃ contents of 5 mol% (**5**) and 15 mol% (**15**) were used for investigations of the sintering behaviour. Powders **5** and **15** were obtained after calcination of [Ba(HOC₂H₄OH)₄][Sn_{0.95}Ge_{0.05}(OC₂H₄O)₃] and [Ba(HOC₂H₄OH)₄][Sn_{0.85}Ge_{0.15}(OC₂H₄O)₃], respectively. The calcination procedure of **5** was as follow: heating at 10 °C/min to 500 °C, then slow heating at 1 °C/min to 850 °C, soaking for 3 h and cooling at 3 °C/min. Powder **15** was obtained in nearly the same manner, however, the precursor was heated up to 860 °C for 10 h. As seen in Fig. 7b, sample **5** consists of a Ba(Sn,Ge)O₃ perovskite phase and a small amount of BaCO₃. Whereas, powder **15** reveals reflections of a Ba(Sn,Ge)O₃ phase, small amounts of BaCO₃ and SnO₂ (Fig. 7a). The specific surface area (BET) of these powders was determined as 15.4 m²/g (**5**) and 15.9 m²/g (**15**), respectively. The equivalent particle size from these BET data was calculated as 55 nm, which can be considered as an average size of the primary particles [55]. Crystallite-size measurements by XRD line broadening [51] of the Ba(Sn,Ge)O₃ reflexions reveal lower values of about $d_{\text{crys.}} = 22$ nm (**5**) and 24 nm (**15**), respectively. Discrepancies between the crystallite-/particle size estimated by the XRD line broadening and the specific surface area were reported and explained elsewhere [43]. The decomposition of the precursor complexes leads to the development of an internal surface in the powder (closely joined crystallites), which is unavailable for nitrogen adsorption. Analogous discrepancies between the particle-/crystallite-size estimated by the XRD line broadening and the specific surface area were also observed in studies of ThO₂ and ZrO₂ [49,56]. TEM images of powder **5** are seen in Fig. 3. The theoretical bulk densities of the resulting ceramic bodies were calculated as 7.12 g/cm³ (**5**) and 6.85 g/cm³ (**15**) [57].

The non-isothermal shrinkage behaviour (dilatometry) of powders **5** and **15** can be seen in Fig. 4. Both powders reveal the beginning of shrinkage at about 1000 °C, however, a significant shrinkage occurs above 1100 °C (**5**) and 1000 °C (**15**), respectively. Powder **15**

begins to shrink at lower temperatures than powder **5**. On the other hand, powder **5** shows a very fast shrinkage process with a shrinkage rate maximum of -7.9 %/min at 1240 °C. The intensity of the shrinkage process of sample **15** is lower. We observe one rate maximum at 1106 °C (-2.5 %/min) and another broad one at 1242 °C (-1.5 %/min). The small difference of the whole shrinkage of both samples is mainly caused by different green densities of the compacts.

The final bulk densities of ceramic bodies (measured from their weight and dimensions) of **5** and **15** after conventional isothermal sintering for 1 and 10 h (heating rate 10 °C/min) are shown in Fig. 5. Dense ceramics (rel. density ≥ 90 %) can be obtained after sintering at a minimum temperature of 1150 °C for 1 h (**5**), which is more than 400 K lower than for nano-BaSnO₃ without any additives [30] (Fig. 5a). The ceramic body reveals cubic grains in a small range between 0.25–0.6 μm (Fig. 6a). A higher BaGeO₃ content of 15 mol% (**15**) needs sintering temperatures considerable above 1150 °C to form dense ceramic bodies. The relative densities of samples **5** and **15** do not differ significantly above a sintering temperature of 1200 °C. Up to 1300 °C ceramic bodies with relative densities of 98–99% can be obtained (Fig. 5a). The final microstructures of ceramics of **5** after sintering of 1 h at 1200 °C show cubic or cuboid-like grains between about 0.25–2 μm , at 1250 °C a bi-modal grain-size distribution with grains between 0.5–5 μm (Fig. 6b), and at 1300 °C we found grains between 1.9–12 μm (Fig. 6c). The microstructures exhibit that small grains have a cubical- or cuboid-like shape, whereas larger grains have an increasingly irregular shape.

A prolonged soaking time of 10 h decreases the minimum sintering temperature for dense ceramic bodies down to 1090 °C (**5**) with grains in the range between 0.35–1 μm (Fig. 5b, 6d). A higher sintering temperature of 1150 °C (10 h) leads to a grain growth with irregular grains between 1.9 and 21 μm (Fig. 6e). Sample **15** requires temperatures above 1120 °C to reach relative densities of ≥ 90 % (Fig. 5b). Compared to the microstructure of ceramics

sintered for 1 h, we found more grains with an irregular shape after the prolonged sintering time. It can be seen that the absolute densities of ceramic bodies of **15** are almost always lower than of bodies of **5**. As mentioned above, sample **15** has only a maximal reachable density of 6.89 g/cm^3 , whereas sample **5** can achieve a maximum density of 7.12 g/cm^3 .

For comparison, BaSnO_3 compacts prepared by a precursor route without any additive show only very moderate sintering behaviour. Sintering temperatures above 1550°C are necessary to reach a relative density of 90 % [30].

Ceramic bodies of **5** exclusively show reflections of the BaSnO_3 phase; no other crystalline phase can be detected (Fig. 7c,d). Consequently, ceramic bodies of **5** consist of a solid solution between BaSnO_3 and BaGeO_3 ($\text{BaSn}_{0.95}\text{Ge}_{0.05}\text{O}_3$) [47]. By contrast, powder patterns of ceramics of **15** clearly indicate reflections of both the $\text{Ba}(\text{Sn,Ge})\text{O}_3$ phase and the orthorhombic BaGeO_3 phase (Fig. 7e–g).

The isothermal sintering results clearly show that dense ceramic bodies can be obtained at sintering temperatures considerable below 1250°C . As reported in ref. [47] BaSnO_3 and BaGeO_3 form a liquid phase at 1270°C . As mentioned above, the non-isothermal dilatometric measurements (Fig. 4) show shrinkage maxima at temperatures $< 1270^\circ\text{C}$ and the maximum shrinkage rates ($\gg 0.1 \text{ %/min}$) suggest that the shrinkage is dominated by sliding processes [58,59]. That means, the formation of a liquid phase is not essential to form dense ceramic bodies and the densification process can be described as a solid-state sintering process. Consequently, the sintering additive BaGeO_3 does not act as a liquid phase former, primarily. BaGeO_3 as well as the small grain size of the preceramic powders (**5**, **15**) improve the sliding processes [60]. Such sliding processes are caused by defect-rich and amorphous (glass-like) contact boundaries, respectively [61,62,63]. Dror et al. [64] could show that these sliding processes (rearrangements) correlate also with the high amount of grain boundaries in nano-powders. They regarded the grain boundaries as amorphous areas surrounding crystalline cores, which promotes the sliding processes.

Conclusion

The sintering temperature of BaSnO₃ or BaSnO₃-based ceramics can be drastically lowered using both nano-sizes powders and the sintering additive BaGeO₃. To combine both effects we synthesized [Ba(HOC₂H₄OH)₄][Sn_{1-x}Ge_x(OC₂H₄O)₃] ($x = 0.05$ (**5**), 0.15 (**15**), 0.25 (**25**)) precursor complexes, which can be decomposed to nano-sized BaSnO₃ powders containing BaGeO₃. The decomposition of precursor **5** finally leads to a single-phase powder indicating a solid solution between BaSnO₃ and BaGeO₃. On the other hand heat treatment of precursor **15** results in a powder and ceramic bodies containing both the Ba(Sn,Ge)O₃ perovskite phase and orthorhombic BaGeO₃. Isothermal sintering experiments of resulting compacts show a drastically reduction of the sintering temperature. Dense ceramic bodies of **5** can be obtained after sintering at 1150 °C for 1 h or at 1090 °C for 10 h, respectively. At these low sintering temperatures the ceramics have cubical-shaped grains between 0.25–0.6 μm and 0.35–1 μm, respectively.

Acknowledgements

Financial support by the Federal State Saxony-Anhalt (Cluster of Excellence "Nanostructured Materials") is gratefully acknowledged.

Fig. 1 XRD patterns of selected precursors. (a) $[\text{Ba}(\text{HOC}_2\text{H}_4\text{OH})_4][\text{Sn}(\text{OC}_2\text{H}_4\text{O})_3]$ (**1**), (b–d) $[\text{Ba}(\text{HOC}_2\text{H}_4\text{OH})_4][\text{Sn}_{1-x}\text{Ge}_x(\text{OC}_2\text{H}_4\text{O})_3]$, (b) $x = 0.05$ (**5**); (c) $x = 0.15$ (**15**); (d) $x = 0.25$ (**25**). The *inset* shows the relationship between the volume of the unit cell and the germanium content (x) of these complexes

Fig. 2 XRD patterns of the $[\text{Ba}(\text{HOC}_2\text{H}_4\text{OH})_4][\text{Sn}_{0.75}\text{Ge}_{0.25}(\text{OC}_2\text{H}_4\text{O})_3]$ precursor (**25**) decomposed at various calcination temperatures (soaking time 1 h, heating rate 10 °C/min)

Fig. 3 TEM images of powder 5

Fig. 4 Non-isothermal dilatometric measurements in air of green bodies of 5 and 15 (heating rate 10 °C/min). The *inset* shows the relative shrinkage rates of these samples

Fig. 5 Evolution of the final densities of some ceramic bodies of 5 and 15 after an isothermal sintering process of a 1 h and b 10 h (rate 10 °C/min)

Fig. 6 SEM images of the surface of ceramic bodies of **5** after various sintering treatments (heating rate 10 °C/min). a 1150 °C, 1 h; b 1250 °C, 1 h; c 1300 °C, 1 h; d 1090 °C, 10 h; e 1150 °C, 10 h

Fig. 7 Graphs (a) and (b) show the XRD patterns of the preceramic powders of precursor **15** (a) and **5** (b) resulting from a heating-rate controlled calcination process at 860 °C for 10 h (**15**) and 850 °C for 3 h (**5**), respectively. Graphs (c–g) represent XRD patterns of ceramic bodies after various sintering procedures. Ceramic **5**: (c) 1100 °C, 10 h; (d) 1300 °C, 1 h. Ceramic **15**: (e) 1150 °C, 10 h; (f) 1250 °C, 1 h; (g) 1300 °C, 1 h

References

- [1] Souza IA, Cavalcante LS, Sczancoski JC, Moura F, Paiva-Santos CO, Varela JA, Simões AZ, Longo E (2009) *J Alloys Compd* 477: 877–882
- [2] Shvartsman VV, Kleemann W, Dec J, Xu ZK, Lu SG (2006) *J Appl Phys* 99: 124111–pp.
- [3] Müllert V, Beige H, Abicht H-P (2004) *Appl Phys Lett* 84: 1341–1343.
- [4] Vivekanandan R, Kutty TRN (1990) *Mater Sci Eng B* 6: 221–231.
- [5] Singh P, Brandenburg BJ, Sebastian CP, Singh P, Singh S, Kumar D, Parkash O (2008) *Jpn J Appl Phys* 47: 3540–3545.
- [6] Movchikova A, Malyskina O, Suchaneck G, Gerlach G, Steinhausen R, Langhammer HT, Pientschke C, Beige H (2008) *J Electroceram* 20: 43–46.
- [7] Wang T, Chen XM, Zheng XH (2003) *J Electroceram* 11: 173–178.
- [8] Kumar A, Singh BP, Choudhary RNP, Thakur AK (2005) *Mater Lett* 59: 1880–1888.
- [9] Prokopalo OI (1976) *Ferroelectrics* 14: 683–685.
- [10] Singh P, Kumar D, Parkash O (2005) *J Appl Phys* 97: 074103pp.
- [11] Brauer H (1970) *Z Angew Phys* 29: 282–287.
- [12] Wang X, Zhou F, Wang Z (2006) *Dianzi Yuanjian Yu Cailiao* 25: 44–46.
- [13] Ostrick B, Fleischer M, Hampe U, Meixner H (1997) *Sens Actuators B* 44: 601–606.
- [14] Tao S, Gao F, Liu X, Sørensen O T (2000) *Sens Actuators B* 71: 223–227.
- [15] Chu X (2004) *Mater Sci Eng B* 106: 305–307.
- [16] Hodjati S, Vaezzadeh K, Petit C, Pitchon V, Kiennemann A (2000) *Catal Today* 59: 323–334.
- [17] Upadhyay S, Kavitha P (2007) *Mater Lett* 61: 1912–1915.

-
- [18] Borse PH, Joshi UA, Ji SM, Jang JS, Lee JS, Jeong E.D, Kim HG (2007) Appl Phys Lett 90: 034103–1pp.
- [19] Yuan Y, Lv v, Jiang X, Li Z, Yu T, Zou Z, Ye J (2007) Appl Phys Lett 91: 094107–1pp.
- [20] Zhang Y, Zhang H, Wang Y, Zhang WF (2008) J Phys Chem C 112: 8553–8557.
- [21] Larramona G, Gutierrez C, Pereira I, Nunes MR, da Costa F M A (1989) J Chem Soc Faraday Trans 85: 907–916.
- [22] Kutty TRN, Vivekanadan R (1987) Mater Res Bull 22: 1457–1465.
- [23] Lu W, Schmidt H (2005) J Eur Ceram Soc 25: 919–925.
- [24] Cerda J, Arbiol J, Diaz R, Dezanneau G, Morante J.R (2002) Mater Lett 56: 131–136.
- [25] Udawatte CP, Yoshimura M (2001) Mater Lett 47: 7–10.
- [26] Udawatte CP, Kakihana M, Yoshimura M (1998) Solid State Ionics 108: 23–30.
- [27] Lu W, Schmidt H (2007) J Sol-Gel Sci Techn 42: 55–64.
- [28] Song YJ, Kim S (2001) J Ind Eng Chem 7: 183–185.
- [29] Jäger L, Lorenz V, Müller T, Abicht H-P, Rössel M, Görls H (2004) Z Anorg Allg Chem 630: 189–195.
- [30] Köferstein R, Jäger L, Zenkner M, Ebbinghaus SG (2009) J Eur Ceram Soc 29: 2317–2324.
- [31] Singh P, Kumar D, Parkash O (2005) J Mater Sci Mater Electron 16: 145–148.
- [32] Upadhyay S, Parkash O, Kumar D (2001) J Mater Sci Mater Electron 12: 165–172.
- [33] Wie X, Yao X (2007) Mater Sci Eng B 137: 184–188.
- [34] Cernea M, Manea A, Piazza D, Galassi C, Vasile E (2007) J Am Ceram Soc 90: 1728–1732.

-
- [35] Azad AM, Hon NC (1998) *J Alloys Compd* 270: 95–106.
- [36] Tien L-C, Chou C-C, Tsai D-S (2000) *Ceram Inter* 26: 57–62.
- [37] Upadhyay S, Parkash O, Kumar D (2001) *Mater Lett* 49: 251–255.
- [38] Rice RW (1998) *Porosity of Ceramics*, ed. Marcel Dekker, New York, pp. 325 et seqq.
- [39] Marković S, Mitrić M, Cvjetićanin N, Uskoković D (2006) *Mater Sci Forum* 518: 241–246.
- [40] Singh P, Parkash O, Kumar D (2005) *Solid State Ionics* 176: 2167–2170.
- [41] He Z, Ma J, Zhang R (2004) *Ceram Inter* 30: 1353–1356.
- [42] Iddles DM, Bell AJ, Moulson AJ (1992) *J Mater Sci* 27: 6303–6310.
- [43] Köferstein R, Jäger L, Zenkner M, Abicht H-P (2008) *J Mater Sci* 43: 832–838.
- [44] Völtzke D, Abicht H.-P (2000) *Solid State Sci* 2: 149–159.
- [45] Kumar A, Choudhary RNP (2007) *J Mater Sci* 42: 2476–2485.
- [46] Wang Z, Zhou F, Chen Z (2006) *Dianzi Yuanjian Yu Cailiao* 25: 58–60.
- [47] Köferstein R, Jäger L, Zenkner M, Müller T, Ebbinghaus SG (2010) *J Eur Ceram* 30: 1419–1425.
- [48] Zenkner M, Jäger L, Köferstein R, Abicht H-P (2008) *Solid State Sci* 10: 1556–1562.
- [49] Allred VD, Buxton SR, McBride JP (1957) *J Phys Chem* 61: 117–120.
- [50] Program WinXPOW v1.06, Stoe & Cie GmbH, Darmstadt (1999).
- [51] Neff H (1959) *Grundlagen und Anwendung der Röntgen-Feinstruktur-Analyse*. R. Oldenbourg, München, p. 287 et seqq.
- [52] Köferstein R, Abicht H-P, Woltersdorf J, Pippel E (2006) *Thermochim Acta* 441: 176–183.
- [53] Köferstein R, Jäger L, Zenkner M, Abicht H-P (2007) *Thermochim Acta* 457: 55–63.

-
- [54] PDF 2 (International Centre for Diffraction Data, Pennsylvania) 2001, BaSnO₃ [15-780], BaCO₃ [5-378], SnO₂ [14-1445], GeO₂ [83-546_{hexagonal}; 73-1306_{tetragonal}], BaGeO₃ [37-137].
- [55] Buscaglia MT, Bassoli M, Buscaglia V, Alessio R (2005) J Am Ceram Soc 88: 2374–2379.
- [56] Garvie RC (1965) J Phys Chem 69: 1238-1243.
- [57] Marks GW, Monson LA (1955) Ind Eng Chem 47: 1611–1620.
- [58] Schatt W (1992) Sintervorgänge. VDI-Verlag, Düsseldorf, pp.78–100.
- [59] Novikov II, Portnoj VK (1984) Superplastizität von Legierungen. Deutscher Verlag für Grundstoffindustrie, Leipzig, p.12 et seqq.
- [60] Köferstein R, Jäger L, Zenkner M, Müller T, Abicht H-P (2008) Mater Chem Phys 112: 531–535
- [61] Geguzin YaE, Klinchuk YuI (1976) Poroshkovaya Metallurgiya 7: 17–25.
- [62] Schatt W (1989) Z Metallkde 80: 809–816.
- [63] Schatt W (1992) Solid State Phenomena 25–26: 23–28.
- [64] Dror Y, Levi RD, Baltianski S, Tsur Y (2006) J Electrochem Soc 153: F137–F143.